

## TIMONOX VINYL MATT

A water-borne matt finish formulated to inhibit the spread of flame on new and previously painted wall and ceiling surfaces including timber based substrates.

### AVAILABILITY

**Colour range** Brilliant White plus 1,126 tintable colours.

**Packaging** 5 litre.

### PROPERTIES

**Drying time** Under normal drying conditions recoatable after 3-4 hours. Allow for adequate ventilation during the drying period

**Finish** Matt.

**Composition** Pigment: Titanium Dioxide, flame retardant additives, extenders and coloured pigments.  
Binder: Chlorinated vinyl copolymer.  
Solvent: Water.

**Spreading rate** Up to 14\* m<sup>2</sup> per litre on a smooth surfaces.

**Wet film thickness** 71\* micrometres @ 14m<sup>2</sup>per litre.

**Dry film thickness** 25\* micrometres @ 14m<sup>2</sup>per litre.

**\*These figures correspond to those quoted on the Fire Test Report and show the minimum film build required.**

**Volume solids** 35%.

**Flash point** Not applicable.

**VOC content** EU limit value for this product (cat.A/i): 140 g/l (2007) / 140 g/l (2010)  
This product contains max. 21 g/l VOC.

**Flame retardancy** When coating new or previously painted combustible and some previously painted non-combustible substrates the use of Timonox Intumescent Basecoat may be required in order to achieve a specific fire rating. See Test Report / Classification table for details.

**Limitations** For interior use only. Do not apply when air or substrate temperatures are likely to fall below 8°C, or when relative humidity is above 80% during application or the drying period.

**Timonox Systems are designed to maintain or improve flame retardancy of a surface. They will NOT impart fire resistance as detailed in BS 476 : 1986 Parts 21-24 or their European equivalent tests.**

### PREPARATION

**New surfaces** All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Powdery, polished plaster or dense surfaces should be primed with Crown Trade Timonox Bonding Primer. Porous surfaces should be mist coated with Crown Trade Timonox Vinyl Matt thinned with up to 20% clean water.

### Bare timber, plywood and MDF

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Rub down with a suitable grade of abrasive paper and round sharp edges 1-3mm. Remove all dust. Treat knots with two thin coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with a proprietary filler. Rub down with a suitable grade of abrasive paper. Remove all dust. Apply two coats of Crown Trade Timonox Intumescent Basecoat.

### Previously decorated surfaces

All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied, e.g dirt, grease etc. Remove all loose, failing or suspect paint. Feather edges of sound paint. Remove all dust. Organic growth must be removed and the areas treated with Crown Trade Fungicidal Solution. Patch prime bare and filled areas with Crown Trade Timonox Bonding Primer thinned as per the container instructions. Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Any glossy or eggshell surfaces should be wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. If after cleaning any areas are still contaminated with substances likely to cause staining and/or bleeding, patch prime with one coat of Crown Trade Timonox Bonding Primer. Bring forward patch primed areas with one coat of Crown Trade Timonox Vinyl Matt. Where necessary apply one coat of Crown Trade Timonox Intumescent Basecoat as outlined in Test Report/Classification table.

### COATING SYSTEMS

Surface	Class	System / spreading rate per coat	Colours	Warringtonfire Test Report number
Paper faced plasterboard	B	1 mist coat Timonox Vinyl Matt. 2 coats Timonox Vinyl Matt @ 14 m <sup>2</sup> per litre per coat.	B/White, Pastel, Tint & Near Neutral Bases	186529
Particleboard	B	2 coats Tim. Intumescent Basecoat @ 5m <sup>2</sup> per litre per coat. 2 coats Timonox Vinyl Matt @ 14 m <sup>2</sup> per litre per coat.	B/White, Pastel, Tint & Near Neutral Bases	186529
Previously decorated paper faced plasterboard. 1 coat alkali resisting primer @ 13 m <sup>2</sup> per litre. 10 coats conventional eggshell @ 14 m <sup>2</sup> per litre per coat.	B	1 coat Tim. Intumescent Basecoat @ 5m <sup>2</sup> per litre per coat. 2 coats Timonox Vinyl Matt @ 14 m <sup>2</sup> per litre per coat.	B/White, Pastel, Tint & Near Neutral Bases	186529
Previously decorated paper faced plasterboard. 1 coat alkali resisting primer @ 13 m <sup>2</sup> per litre. 10 coats conventional eggshell @ 14 m <sup>2</sup> per litre per coat.	0	2 coats Timonox Vinyl Matt @ 14 m <sup>2</sup> per litre per coat.	B/White, Pastel, Tint & Near Neutral Bases	185837 & 185838
Warrington Blueboard Class 4 Upgrade	0	2 coats Timonox Intumescent Basecoat @ 5m <sup>2</sup> per litre per coat. 2 coats Timonox Vinyl Matt @ 14 m <sup>2</sup> per litre per coat.	B/White, Pastel, Tint & Near Neutral Bases.	185847 & 185848

**APPLICATION** Stir well before use. Apply by brush, roller, or airless spray (thinning may be required). For spray application refer to the Crown Trade Timonox Airless Spray Application Guidelines (Technical Data Sheet)

**Note: When thinning an additional coat may be required to achieve the specified film build and subsequent fire protection.**

**CLEANING** Return surplus material to container. Wash with clean water immediately after use.

**MAINTENANCE INFORMATION FOR CDM FILE**

Between maintenance redecoration surfaces may be washed with a warm water and liquid detergent solution to remove surface dirt.

**HEALTH AND SAFETY**

Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact our Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

**GENERAL INFORMATION**

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by the manufacturer as it has no control over the conditions under which its products are applied.

For help or more information contact our Customer Relations Team on 0845 389 9583. Before using this product please ensure you have the latest information. The information is correct at date of issue April 2010.



**Crown Paints Ltd**

Crown House, Hollins Road, Darwen, Lancs BB3 0BG

Tel: 0845 389 9583 Fax: 0845 389 9584 Email: [info@crowntrade.co.uk](mailto:info@crowntrade.co.uk)

Website: [www.crowntrade.co.uk](http://www.crowntrade.co.uk)